



Product Data Sheet

EcoSoya Pillar Blend (PB)

Product Description

Soy wax.

Technical Properties

Analysis	Typical	Method
Mettler Drop Point	129°F (53.9°C)	AOCS Cc 18-80
Congeaing Point	124°F (51.1°C)	ASTM D 938-60
Needle Penetration (1/10 mm)	21	ASTM D 1321-65
Color, Red	3.5 Max	AOCS Cc 13b-45

Suggested Applications/Possible Uses

Pillar and Molded Candles including: Votives, Tarts, Melts, and Novelty, as well as Container Candles and other applications.

Shelf Life

Solid Wax

No determined shelf life if stored under proper conditions.

Liquid Wax

Two to Four weeks under proper storage conditions.

Shipping and Storage

Solid Wax

Store in a cool, dry location away from direct heat, sunlight, and moisture. Temporary hot or cold temperature extremes have no adverse effect. EcoSoya waxes may be used frozen and, if partially melted, allow to cool, and re-solidify before use.

Liquid Wax

Liquid wax should be shipped under a nitrogen blanket and have no contact with brass or copper. For storage, wax should be kept just above the melting point with no agitation, under nitrogen blanket, and have no contact with brass or copper.

The Soap Kitchen
Unit 8 Caddsdwn Industrial Park, Clovelly Road, Bideford,
Devon EX39 3DX
Tel: 01237 420872 (+44 (0)1237 420872)
Email: it@thesoapkitchen.co.uk